

Ref #	Hits	Search Query	DBs	Default Operator	Plurals	Time Stamp
L2	4547	257/40.ccls. 257/66.ccls. 257/75.ccls. 257/347.ccls. 257/e51.006.ccls. 438/99.ccls.	US-PGPUB; USPAT	OR	OFF	2005/06/17 09:40
L3	687	L2 and (polythiophene p3ht ((conjugat\$5 organiz\$6 "self-organizable") near polymer))	US-PGPUB; USPAT	OR	ON	2005/06/17 09:50
L5	101	(polythiophene ((conjugat\$5 organiz\$6 "self-organizable") near polymer)) and (agitat\$6 stir\$6 sonicat\$6 homogen\$10)	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2005/06/17 11:59
L6	2	(((((polymer with dissolv\$5) same (agitat\$6 stir\$6 sonicat\$6 homogen\$10)) same (temperature near2 (lower\$4 reduc\$6 decreas\$5 room))) same (coat\$5 deposit\$5 layer film)) same (gel\$6 near2 (avoid\$5 disrupt\$5 imped\$5 stop\$5 inhibit\$5)))	US-PGPUB; USPAT	OR	ON	2005/06/17 12:03
L7	205	((polymer with dissolv\$5 with (temperature heat\$5)) same ((agitat\$6 stir\$6 sonicat\$6 homogen\$10) with (temperature near2 (lower\$4 reduc\$6 decreas\$5 room)))) same (gel\$6 coat\$5 deposit\$5 layer film)	US-PGPUB; USPAT	OR	ON	2005/06/17 12:06
L8	109	((polymer with dissolv\$5) and (agitat\$6 stir\$6 sonicat\$6 homogen\$10)) and (temperature near2 (lower\$4 reduc\$6 decreas\$5 room))) and (gel\$6 coat\$5 deposit\$5 layer film)	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2005/06/17 12:13
L9	26	((polymer with dissolv\$5 with (temperature heat\$5)) same ((sonicat\$6 homogen\$10) with (temperature near2 (lower\$4 reduc\$6 decreas\$5 room)))) same (gel\$6 coat\$5 deposit\$5 layer film)	US-PGPUB; USPAT	OR	ON	2005/06/17 12:15
L10	27	((polymer with dissolv\$5 with (temperature heat\$5)) same ((sonicat\$6 homogen\$10) with stir\$6 with (temperature near2 (lower\$4 reduc\$6 decreas\$5 room))))	US-PGPUB; USPAT	OR	ON	2005/06/17 12:16
L11	46	(polymer with dissolv\$5 with (temperature heat\$5)) same (water alcohol liquid) same ((coat\$5 deposit\$5 layer film) with spin\$6)	US-PGPUB; USPAT	OR	ON	2005/06/17 12:18

L12	15	(polymer with thixotrop\$8 with gel\$8) same (agitat\$6 stir\$6 sonicat\$6 homogen\$10)	US-PGPUB; USPAT	OR	ON	2005/06/17 12:22
L13	63	(polythiophene conjugat\$5 organiz\$6 "self-organizable") with (polyphosphazene phosphazene)	US-PGPUB; USPAT	OR	ON	2005/06/17 12:23
L15	182	L2 and ((polythiophene p3ht ((conjugat\$5 organiz\$6 "self-organizable") near polymer)) with semiconductor)	US-PGPUB; USPAT	OR	ON	2005/06/17 12:26
L16	244	L2 and ((polythiophene p3ht ((conjugat\$5 organiz\$6 "self-organizable") near polymer)) with semiconduct\$6)	US-PGPUB; USPAT	OR	ON	2005/06/17 12:46
L17	62	L16 not L15	US-PGPUB; USPAT	OR	ON	2005/06/17 12:55
L18	31	L2 and ((polythiophene p3ht ((conjugat\$5 organiz\$6 "self-organizable") near polymer)) same (coalesc\$6 aggregat\$6 (structur\$6 near order\$6)))	US-PGPUB; USPAT	OR	ON	2005/06/17 12:57
L19	229	((polythiophene p3ht ((conjugat\$5 organiz\$6 "self-organizable") near polymer)) with (coalesc\$6 aggregat\$6 (structur\$6 near order\$6)))	US-PGPUB; USPAT	OR	ON	2005/06/17 12:58
L21	7	(polythiophene p3ht ((conjugat\$5 organiz\$6 "self-organizable") near polymer)) same (coalesc\$6 aggregat\$6) same (structur\$6 near order\$6)	US-PGPUB; USPAT	OR	ON	2005/06/17 10:32
L22	44	((polythiophene p3ht ((conjugat\$5 organiz\$6 "self-organizable") near polymer)) and (coalesc\$6 aggregat\$6 (structur\$6 near order\$6)))	EPO; JPO; DERWENT; IBM_TDB	OR	ON	2005/06/17 11:20
L23	31	L2 and ((polythiophene p3ht ((conjugat\$5 organiz\$6 "self-organizable") near polymer)) same (coalesc\$6 aggregat\$6 (structur\$6 near order\$6)))	US-PGPUB; USPAT	OR	ON	2005/06/17 10:27
L24	2	wo-9954936-\$.did.	US-PGPUB; USPAT; EPO; JPO; DERWENT	OR	OFF	2005/06/17 10:28
L25	133	((polythiophene ((conjugat\$5 organiz\$6 "self-organizable") near polymer)) same (agitat\$6 stir\$6 sonicat\$6 homogen\$10)) same (gel\$6 coat\$5 deposit\$5 layer film)	US-PGPUB; USPAT	OR	ON	2005/06/17 11:45